



Realiz Ltd

info@realiz.al

www.realiz.al

*Moving mountains,
one stone at a time.*

Realiz is fully integrated supplier of Melove marbled limestone. From raw block, slab material, and standard products, we are a leading supplier of the nation's stone. Since our founding in 2017, we continue to be the best limestone quarrier and fabricator in Albania. At Realiz, our strength is in our reliability as we consistently provide high quality products and services to meet your needs.

If you are irritated by every rub,
how can you be polished? - Rumi



www.realiz.al





White & Unique Perla

Limestone is one of the most versatile stones which is sturdy and easy to maintain. White & Unique Perla is a beige limestone from the picturesque Tomor Mountain Ranges in Skrapar, Albania. The very pleasing light-toned material can be offered in various finishes from polished, honed (matt), brushed, antiquated to rough.

ARP3012: White & Unique Perla - First Commercial

ARP3014: White & Unique Perla Extra

ARP3015: White & Unique Perla

ARP3022: White & Unique Perla - Brushed

ARP3012

ARP3014

ARP3015

ARP3022

Did you now?
The original
casing stones were
made of highly
polished limestone,
meant to reflect
the suns rays,



Limestone is very
important in construction
and architecture. It is often
used as the main material
to create floor tiles, stair
treads, window sills and
facing stones.



MATERIAL DATA SHEET			
Stone Name	Crema Illyria		
Structure	Limestone		EN 12407
Application	Slabs for floors and stairs		EN 12058
	Slabs for internal paving		EN 1469
	Slabs for cladding		EN 12057
	Slabs for internal wall and ceiling		EN 1341
Apparent Density	2.610	Kg/m³	EN 1936
Open Porosity	3,3	%vol	EN 1936
Water Absorption	1,1	%weight	EN 13755
Water Absorption By Capillarity	2,267	g/(m²/sec)	EN 1925
Breaking Load At Dowel Hole - Average - Min Expected Value - Standard Deviation	1.850 1.444 200	N N N	EN 13364
Flexural Strength Under Concentrated Load - Average - Min Expected Value - Standard Deviation	13,1 10 1,5	Mpa Mpa Mpa	EN 12372
Flexural Strength 12 Frost Cycles - Standard Deviation	10,9 3,7	Mpa Mpa	EN 12371
Flexural Strength 48 Frost Cycles - Standard Deviation	14,4 0,9	Mpa Mpa	EN 12371
Abrasion Resistance	23.819	mm³	EN 14157 B
Resistance To Ageing By Thermal Shock	-0,01	%	EN 14066
Slip / Skid Resistance SRV - Dry Polished - Wet Polished - Dry Honed - Wet Honed - Dry Rough - Wet Rough	51 4 64 16 58 52		EN 14231
Test Results Provided By	Insitute Of Geology & Mineral Exploration Ornamental Stone Quality Control Laboratory “LITHOS” Certificate 70-3 ELOT EN ISO/IEC 17025		
Test results are related with tested samples only and may be used as guidance of the material's properties			



Office

Address: Kavaja Street, Tirana

Address: Street "3 Deshmoret", Kashar, Tirana

Contact

Mobile: +355 69 614 2222

Email: info@realiz.al